

MOLYKOTE® G-4700 Extreme Pressure Synthetic Grease

Features

- Wide service-temperature range
- Compatible with many plastics and elastomers
- Meets Cincinnati Machine P-64 and NLGI GC-LB
- Fully synthetic base oil

Benefits

- Formulated to provide higher load-carrying capacity, greater wear resistance and longer service life compared to conventional petroleum-based lubricants
- Provides good compatibility with most industrial and engineering substrates, including many plastic and rubber materials
- Designed to handle extreme loads and applications involving vibration and/or shock loading
- Excellent low-temperature torque

Composition

- PAO base oil
- Lithium complex thickener
- Fortified with molybdenum disulfide (MoS₂)

Applications

General purpose light-consistency black synthetic grease can be used in rolling element and plain bearings, pivot pins, cams, guides, ways, drive screws, gears, splines, and other machine elements.

Description

MOLYKOTE® G-4700 Extreme Pressure Synthetic Grease combines the benefits of wide operating-temperature range and broad compatibility with varied materials. It is thickened with a lithium complex and contains molybdenum sulfide as a solid lubricant. MOLYKOTE® G-4700 Grease can be used to lubricate rolling element and plain bearings, pivot pins, cams, guides, ways, drive screws, gears, splines and other machine elements.

How to use

Apply using conventional grease application methods (i.e., clean brush, grease gun and manual or automated dispensing equipment).

Typical properties

Specification writers: These values are not intended for use in preparing specifications. Please contact your local MOLYKOTE® sales representative prior to writing specifications on this product.

Standard ⁽¹⁾	Test	Unit	Result
Consistency, viscosity, specific gravity			
DIN 51 818	NLGI consistency class		2
ASTM D217	Penetration at 25°C (77°F) (W/60)	mm/10	265-295
ASTM D445	Base oil viscosity at 40°C (104°F)	cSt	150
ASTM D445	Base oil viscosity at 100°C (212°F)	cSt	20
ISO 2811	Specific gravity at 25°C (77°F)	g/ml	0.87
Temperature			
	Temperature range (approximate)	°C	-40 to 177
		°F	-40 to 350
ASTM D2265	Dropping point	°C	>285
		°F	>545
FD 791-32/2	Oil bleed, 24 hours, 100°C (212°F)	wt%	3.9
FD 791-32/2	Oil evaporation, 24 hours, 100°C (212°F)	wt%	0.44
ASTM D4693	Low-temperature torque at -40°C (-40°F)	Nm	.024
Load-carrying capacity, wear protection, speed			
ASTM D2266	Four-ball wear, 40 kg, 1,200 rpm	mm	0.64
ASTM D2596	Four-ball EP, weld load, minimum	N	3,700
	Dn, bearing ID (mm)x(rpm), estimated		350,000

⁽¹⁾DIN: Deutsche Industrie Norm. ASTM: American Society for Testing and Materials. ISO: International Standardization Organization. FD: Federal Standard: Testing Method of Lubricants Liquid Fuels and Related Products.

Handling precautions

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION.

Usable life and storage

When stored at or below 35°C (95°F) in the original unopened containers, these products have a usable life of 60 months from the date of production.

Packaging

This product is available in different standard container sizes. Detailed container size information should be obtained from your nearest MOLYKOTE® sales office or MOLYKOTE® distributor.

*DuPont™, the DuPont Oval Logo, and all trademarks and service marks denoted with ™, SM or ® are owned by affiliates of DuPont de Nemours, Inc. unless otherwise noted.
© 1999-2019 DuPont.*

The information set forth herein is furnished free of charge and is based on technical data that DuPont believes to be reliable and falls within the normal range of properties. It is intended for use by persons having technical skill, at their own discretion and risk. This data should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents.